


900 μ mチューブ
0.9mm Tubing - TEFLON PVDF



Dimension of Tubing

Outer Diameter	900 +/-50 μ m	Inner Diameter	500 +/-50 μ m
----------------	-------------------	----------------	-------------------

Material Properties

Material	Properties	Value	Unit	Test Method
PVDF	Tensile Modulus	150-220	kpsi	ASTM D638
	Tensile Strength at Break	4000-7000	psi	ASTM D638
	Elongation at Break	2100	%	ASTM D638
	Hardness	70-75	Shore D	
	Water Absorption	<0.05	%	ASTM D2240
	Shrinkage	2.0%		FOTP-86
	Vertical Burn	V0		UL94
	Operating Temperature	-40~+125C		

* 特注チューブの製作も可能です。詳細は、お手数ですがお問い合わせフォームにお願いします。

Contact your OSTenp representative for information on specifications and availability.