

900 $\mu$ mチューブ  
0.9mm Tubing - TEFLON PTFE



Dimension of Tubing			
Outer Diameter	900 $\pm$ 100 $\mu$ m	Inner Diameter	450 $\pm$ 50 $\mu$ m

Material Properties				
Material	Properties	Value	Unit	Method
PTFE	Tensile Strength	30	MPa	ASTM D638
	Elongation	300	%	ASTM D638
	Coefficient of Friction, Dynamic	0.1	< 3 m/min	ASTM D1894
	Upper Service Temperature (20000 hrs)	260	$^{\circ}$ C	UL 746B
	Water Absorption	< 0.01	%	ASTM D570
	Flammability	V0		UL 94
	Coefficient of Linear Expansion	10	$10^{-5}/^{\circ}$ C	ASTM D635
	Appearance	Translucent		
	FiTek's Part Number	T009PTNW		

\* 特注チューブの製作も可能です。詳細は、お手数ですがお問い合わせフォームをお願いします。

Contact your OSTenp representative for information on specifications and availability.